
# **BGH-6100F2**


(6V 12Ah)

Rechargeable Sealed Lead Acid Battery (High Rate Series)














General Series Valve Regulated Lead Acid batteries are designed with AGM (Absorbent Glass Mat) technology, high performance plates and electrolyte to gain extra power output for many commonly used applications. Special one-way valves allow excessive gases to escape but otherwise the battery is completely sealed and therefore maintenance-free, leak proof and usable in any position



## **Application**

- · Alarm System
- · Cable Television
- · Communication Equipment
- · Control Equipment
- · Security System
- · Medical Equipment
- ·UPS
- · Emergency Power System
- Tovs

#### **Performance Characteristics**

Designed Floating Life	5 Years						
Capacity	20HR(0.67A,1.75V)	10HR(1.32A,1.75V)	5HR(2.25A,1.75V)	1HR(8.6A,1.75V)			
(25°C)	12.2AH	12AH	11AH	8AH			
Dimensions	Length	Width	Height	Total Height			
Difficusions	151mm(5.94inch)	50mm(1.97inch)	95mm(3.74inch)	101mm(3.98inch)			
Approx. Weight	1.66kg(3.66lbs)						
Internal Resistance	Full charged at 25°C: 0.01 Ohm						
Self Discharge	3% of capacity declined per month at (25°C)						
Capacity	40°C	-15°C					
Affected by Temp. (20HR)	102% 100%		85%	65%			
Charge	Cycle	e use	Float use				
<b>Voltage</b> (25°C)		15mV/°C), rrent: 4A	6.8-6.9V(-10mV/°C)				

#### **General Features**

- Superb high-rate discharge characteristics that ensure reliable performance in UPS applications.
- Sealed non-spillable maintenance free operation.
- Flexible installation in any position.
- ABS containers and covers (UL94HB, UL94V0) optional.
- VRLA Absorbent Glass Mat (AGM) Technology guarantees safe operation without maintenance.
- Approved for transport by air. D.O.T., I.A.T.A. and F.A.A. certified.
- High quality and high reliability.
- Exceptional deep discharge recovery performance.
- Low self-discharge characteristics

Battery Construction									
Component Positive plate Negative plate Container Cover Safety valve Terminal Separator Electrolyte								Electrolyte	
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid	

batteryguy.com


Toll Free: 800-572-1975

(Note) The above characteristics data are average values obtained within three charge/discharge cycles not the minimum values.


Page 1 of 2




#### **Charge characteristic**




### Discharge characteristic (25°C)



## Relationship of OCV and state of charge



Self-discharge characteristic



STORAGE TIME: MONTHS

Constant current discharge ratings (Amperes at 77°F 25°C)									
F.V/Tim e	5 min	10 min	15 min	30 min	1HR	3HR	5HR	10HR	20HR
1.60V	65.0	40.4	30.5	18.6	9.38	4.12	2.52	1.37	0.74
1.67V	61.0	38.4	29.3	17.8	9.26	3.96	2.46	1.36	0.71
1.70V	55.9	37.0	28.7	16.2	8.98	3.70	2.41	1.35	0.70
1.75V	54.8	35.8	27.7	15.4	8.55	3.57	2.36	1.35	0.69
1.80V	49.0	34.2	25.2	14.2	8.01	3.43	2.22	1.32	0.67
1.85V	43.3	32.6	22.6	13.1	7.46	3.31	2.08	1.30	0.65

Constant power discharge ratings (Watts at 77°F 25°C)									
F.V/Tim e	5 min	10 min	15 min	30 min	1HR	3HR	5HR	10HR	20HR
1.60V	114.0	73.0	55.7	33.5	16.9	7.30	4.25	2.82	1.48
1.67V	110.0	71.2	55.0	32.8	16.8	7.08	4.24	2.80	1.43
1.70V	103.6	70.5	54.5	30.7	16.5	6.76	4.18	2.78	1.41
1.75V	104.3	70.3	54.1	29.8	16.2	6.60	4.14	2.75	1.37
1.80V	95.4	69.2	50.1	28.4	15.3	6.41	4.02	2.71	1.34
1.85V	86.5	65.7	45.5	26.6	14.4	6.21	3.89	2.62	1.32

Page 2 of 2 batteryguy.com

Toll Free: 800-572-1975