BG-6100F1

(6V 12Ah)


Rechargeable Sealed Lead Acid Battery






Rechargeable Sealed Lead Acid Battery


6 volt 12 Ah








These rechargeable batteries are lead-lead dioxide systems. The dilute sulfuric acid electrolyte is absorbed by separators and thus immobilized. Should the battery be accidentally overcharged producing hydrogen and oxygen, special one-way valves allow the gases to escape thus avoiding excessive pressure build-up. Otherwise, the battery is completely sealed and is, therefore, maintenance-free, leak proof and usable in any position.





- · Alarm System
- · Cable Television
- · Communication Equipment
- · Control Equipment
- · Security System
- · Medical Equipment
- · UPS
- · Power tools
- · Emergency Power System
- · Toys

Performance	Characteristics

Designed Floating Life	5 Years					
Capacity	20HR(0.6A,1.75V)	10HR(1.15A,1.75V)	5HR(2.04A,1.75V)	1HR(7.8A,1.75V)		
(25°C)	12AH	11.5AH	10.2AH	7.8AH		
Dimensions	Length	Width	Height	Total Height		
Difficitions	150.5mm(5.93inch)	50mm(1.97inch)	94mm(3.70inch)	100mm(3.94inch)		
Approx. Weight	2.0Kg (4.41lbs)					
Internal Resistance	Full charged at 25°C: 0.010 Ohm					
Self Discharge	3% of capacity declined per month at (25°C)					
Capacity	40°C	25°C	0°C	-15°C		
Affected by Temp. (20HR)	102%	100%	85%	65%		
Charge	Cycle	e use	Float use			
Voltage (25°C)		15mV/°C), rent: 3.6A	6.8-6.9V(-10mV/°C)			

General Features

- Absorbent Glass Mat(AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.


Battery Construction									
Component Positive plate Negative plate Container Cover Safety valve Terminal Separator E							Electrolyte		
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid	




Charge characteristic

Charge Capacity Constant Charge At 0.25CA-2.30V (25°C) (%) (CA) (V/Cell) 120 Charge Voltage 2.33 100 Charge Capacity 80 2.17 0.25 100% Discharge 0.20 60 2.00 50% Discharge 0.15 40 0.10 1.83 20 0.05 **Charge Current** 0_ 0 10 TIME (HOURS)


Discharge characteristic (25°C)



Relationship of OCV and state of charge



Self-discharge characteristic



Constant current discharge ratings (Amperes at 77°F 25°C)									
F.V/Tim e	5 min	10 min	15 min	30 min	1HR	3HR	5HR	10HR	20HR
1.60V	46.9	29.2	22.0	13.4	8.53	3.74	2.29	1.28	0.67
1.67V	44.0	27.7	21.2	12.8	8.42	3.60	2.24	1.27	0.65
1.70V	40.3	26.7	20.7	11.7	8.16	3.36	2.19	1.26	0.64
1.75V	39.5	25.8	20.0	11.1	7.78	3.25	2.14	1.25	0.62
1.80V	35.4	24.7	18.2	10.3	7.28	3.12	2.02	1.23	0.61
1.85V	31.2	23.5	16.3	9.45	6.78	3.01	1.89	1.21	0.59

Consta	Constant power discharge ratings (Watts at 77°F 25°C)								
F.V/Tim e	5 min	10 min	15 min	30 min	1HR	3HR	5HR	10HR	20HR
1.60V	82.2	52.7	40.2	24.2	15.4	6.64	3.87	2.56	1.34
1.67V	79.4	51.3	39.7	23.7	15.3	6.43	3.85	2.54	1.30
1.70V	74.7	50.8	39.3	22.2	15.0	6.14	3.80	2.53	1.28
1.75V	75.2	50.7	39.0	21.5	14.8	6.00	3.77	2.50	1.25
1.80V	68.8	49.9	36.2	20.5	13.9	5.82	3.65	2.46	1.22
1.85V	62.4	47.4	32.8	19.2	13.1	5.65	3.53	2.43	1.17

Page 2 of 2